

Hycrete Installation

- Hydrophobic admixture for mortar is a liquid admixture that is added to mortar mix at dosage of 2 liters per cubic meter of mortar. **Contact manufacturer for specific dosage questions according to design.**
- Trial batches are strongly recommended to assess the local plastic and hardened properties and to determine appropriate mix designs.
- It may be appropriate to remove a similar amount of water from the mortar mix as the amount of hydrophobic admixture added.
- Allow hydrophobic admixture to thoroughly mix in mortar mix
- Install mortar as normal.
- For increased water resistance performance, apply mortar to a greater thickness in accordance with project guidelines (see ASTM C926 for more details on application).
- Discard any materials that show signs of stiffening or setting – do not wet up by adding water.
- Moist cure mortar in accordance with ACI 308; if moist curing is not possible, use curing compound complying with ASTM C309.